

TECHNICAL DATA SHEET

Composed of PebbleTec's finest aggregate and engineered for enhanced durability, **PebbleFina®** delivers an exceptionally smooth surface finish built to last.

- **Longevity:** Designed for decades of performance.
- **Look & Feel:** Smooth, refined surface texture.
- **Warranty:** 5-year product warranty with registration and 5-year workmanship warranty.

**All pool finishes require maintenance of proper pool water chemistry for maximum lifespan.*



Classico



Acquos



Bella Blue



Cielo Blue

COLOR LIGHTNESS ANALYSIS

 PebbleFina® Enduring Smooth Finish	DRY				WET			
	CIE VALUES			LRV	CIE VALUES			LRV
	L*	a*	b*		L*	a*	b*	
Classico	90.70	-0.95	3.30	77.80	86.68	-1.22	5.15	69.40
Cielo Blue	87.19	-0.20	3.12	70.40	83.11	-0.11	4.55	62.40
Bella Blue	84.34	-3.56	-3.63	64.70	78.39	-4.29	-3.98	53.90
Acquos	86.04	-4.06	1.07	68.10	79.17	-5.91	1.89	55.20
Report Date: Feb 2018, Completed by CTL Group								

ANALYSIS NOTES

The samples were submitted as cast mortar tiles with formed side and bottom surfaces. The top surfaces were a hard-troweled finish. Measurements were first taken on the dry top surfaces. The surfaces were then placed under running water for approximately 15 seconds, lightly blotted to remove excess surface moisture, and re-tested in the wet condition. This analysis represents specifically the samples submitted.

ANALYSIS INFORMATION

CIE Illuminant/Standard Observer: D65/10° (daylight 6500k, 10° observer).

Description of CIE Values: L* = lightness from black (0) to white (100); a* = green (-a) to red (+a); b* = blue (-b) to yellow (+b).

LRV = Light Reflectance Value: LRV is the measured CIE Y value.

Lightness and LRV Values: Were determined by utilization of ASTM E1347 and ASTM E1477. Testing is explained in ASTM D4086.

COMPRESSIVE STRENGTH		TENSILE STRENGTH		DRYING SHRINKAGE		COEFFICIENT OF FRICTION	
ASTM Spec C 109		ASTM Spec C 307		ASTM Spec C 596		ASTM Spec C 1028	
7 Day	6,124 psi	28 Day	634 psi	7 Day	0.0893%	Static Dry	0.69
18 Day	6,911 psi	—	—	14 Day	0.1290%	Dynamic Dry	0.62
90 Day	9,271 psi	—	—	21 Day	0.1508%	Dynamic Wet	0.58
—	—	—	—	28 Day	0.1648%	—	—

PebbleTec.com

8435 N 90th St., Suite 6, Scottsdale, AZ 85258

Contact your PebbleTec Representative or call Customer Service at 800-937-5058.