

TECHNICAL DATA SHEET

PebbleTec’s most popular pool finish, **PebbleSheen®** offers a natural pebble appearance with a refined, comfortable texture suited for a wide range of pool applications.

- **Longevity:** Designed for decades of performance with minimal maintenance.
- **Look & Feel:** Natural pebble appearance with a refined, comfortable surface texture.
- **Warranty:** 5-year product warranty with registration and 5-year workmanship warranty.

*\*All pool finishes require maintenance of proper pool water chemistry for maximum lifespan.*



Cool Blue



Arctic White



White Diamonds



Commercial White

COLOR LIGHTNESS ANALYSIS

| <br>PebbleSheen®<br>Refined Textured Finish | DRY        |       |      |       | WET        |       |      |       |
|-------------------------------------------------------------------------------------------------------------------------------|------------|-------|------|-------|------------|-------|------|-------|
|                                                                                                                               | CIE VALUES |       |      | LRV   | CIE VALUES |       |      | LRV   |
|                                                                                                                               | L*         | a*    | b*   |       | L*         | a*    | b*   |       |
| Cool Blue                                                                                                                     | 86.81      | -0.47 | 4.59 | 69.60 | 81.52      | -0.75 | 6.50 | 59.41 |
| Arctic White                                                                                                                  | 85.96      | -0.53 | 4.39 | 67.90 | 81.13      | -0.45 | 6.75 | 58.70 |
| White Diamonds                                                                                                                | 83.80      | 0.35  | 5.56 | 64.40 | 75.22      | -0.44 | 8.98 | 52.62 |
| Commercial White WP-4/AW-3                                                                                                    | 85.29      | -0.28 | 5.93 | 66.30 | 80.90      | -1.45 | 7.28 | 54.03 |
| Report Date: September 2025, Completed by CTL Group                                                                           |            |       |      |       |            |       |      |       |

ANALYSIS NOTES

The samples were submitted as cast mortar tiles with formed side and bottom surfaces. The top surface of each sample is slightly rough compared to the bottom surface. The evaluation was first taken on the dry top surface. The surface was then placed under water for approximately 15 seconds, lightly blotted to remove excess surface moisture, and re-tested in the wet condition.

ANALYSIS INFORMATION

- Instrument: X-Rite® Sphere Spectrophotometer, Model Ci62, Serial Number 013714.
- Specular component included.
- For each condition, three measurements were taken over the surface of the sample; reported values represent the average of these measurements.

CIE Illuminant/Standard Observer: D65/10° (daylight 6500k, 10° observer).

Description of CIE values: L\* = lightness from black (0) to white (100); a\* = green (-a) to red (+a); b\* = blue (-b) to yellow (+b).4.

LRV = Light Reflectance Value: = light reflectance value. LRV is the measured CIE Y value.

| COMPRESSIVE STRENGTH |           | TENSILE STRENGTH |         | DRYING SHRINKAGE |        | COEFFICIENT OF FRICTION |      |
|----------------------|-----------|------------------|---------|------------------|--------|-------------------------|------|
| ASTM Spec C 109      |           | ASTM Spec C 307  |         | ASTM Spec C 596  |        | ASTM Spec C 1028        |      |
| 7 Day                | 7,450 psi | 28 Day           | 601 psi | 7 Day            | 0.095% | Static Dry              | 0.67 |
| 28 Day               | 8,440 psi | —                | —       | 14 Day           | 0.123% | Dynamic Dry             | 0.61 |
| 90 Day               | 9,400 psi | —                | —       | 21 Day           | 0.143% | Dynamic Wet             | 0.63 |
| —                    | —         | —                | —       | 28 Day           | 0.151% | —                       | —    |